

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08G 18/81, 18/67, C09D 175/16, C03C 25/10	A1	(11) International Publication Number: WO 00/02943 (43) International Publication Date: 20 January 2000 (20:01:00)
(21) International Application Number: PCT/NL99/00423 (22) International Filing Date: 5 July 1999 (05.07.99) (30) Priority Data: 10/193104 8 July 1998 (08.07.98) JP (71) Applicants (for all designated States except US): DSM N.V. [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL). JSR CORPORATION [JP/JP]; JSR Building, 2-11-24, Tsukiji, Chuo-ku, Tokyo 104-8410 (JP). (72) Inventors; and (75) Inventors/Applicants (for US only): HIRAI, Tsuyoshi [JP/JP]; 2-13-28, Kawaguchi, Tsuchiura City 300 (JP). KOMIYA, Zen [JP/JP]; 2-18-33, M1-3 Umezono, Tsukuba, Ibaraki 305 (JP). UKACHI, Takashi [JP/JP]; 5-22-9, Kamiya, Ushiku 300-12 (JP). (74) Agent: DEN HARTOG, Jeroen, Hendrikus, Joseph; Octrooibureau DSM, P.O. Box 9, NL-6160 MA Geleen (NL).		(81) Designated States: CN, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: PHOTOCURABLE RESIN COMPOSITION (57) Abstract A photocurable resin composition with small water absorption, low viscosity, and high curing speed, which is suitable as a coating material for optical fibers. The photocurable resin composition comprising a urethane (meth)acrylate as a polymerizable component, wherein part or all of the urethane (meth)acrylate is produced from 12-hydroxystearic acid triglyceride.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

PHOTOCURABLE RESIN COMPOSITION5 Field of the Invention

The present invention relates to a photocurable resin composition and, more particularly, to a photocurable resin composition having low viscosity and exhibiting a high curing speed, while
10 producing cured products with small water absorption. In particular, the curable composition of the present invention is a liquid curable composition that can be formulated for use in a wide variety of applications including, for example, coatings and/or binders. In
15 particular, these curable compositions offer relatively fast cure speeds which offer advantages in many applications such as in the production of fiber optics wherein production speeds make it desirable to utilize primary coatings, secondary coatings (including, for
20 example transparent and/or colored secondary coatings), inks, matrix materials and/or bundling materials that can be cured rapidly.

Background of the Invention

25 In the production of optical fibers, a resin coating is provided for protection and reinforcement immediately after spinning molten glass fibers. A known structure of the resin coating consists of a primary coating layer of a flexible resin coated
30 on the surface of the optical fibers and a secondary coating layer of a rigid resin provided over the

primary coating layer. A so-called optical fiber ribbon has been known in the art in the application of optical fibers provided with a resin coating. The optical fiber ribbon is made from several optical fibers (e.g. four
5 or eight optical fibers) by arranging these fibers in a plane and securing them with a binder to produce a ribbon structure with a rectangular cross section. A method for fabricating a multi-core structure by bundling two or more such ribbons has also been known
10 in the art. For example, two ribbons each consisting of four optical fibers are covered altogether with the binder to form a ribbon with eight optical fibers. A resin composition for forming the primary coating layer is called a primary coating; a resin composition for
15 forming the secondary coating layer is called a secondary coating; a material for producing the optical fiber ribbon structure from several optical fibers is called a ribbon matrix material; and a material for further binding several optical fiber ribbons to
20 produce multi-core optical fiber ribbons is called a bundling material. Often, the fibers for identification purposes will be further coated with an ink, which is a curable resin comprising a colorant (such as a pigment and/or a dye), or the secondary coating may be a
25 colored secondary coating (i.e., comprise a colorant).

Photocurable compositions have conventionally been used as a resin composition for optical fiber coatings in view of high productivity. A typical composition comprises a urethane
30 (meth)acrylate, (meth)acrylate monomer (a relatively low molecular weight compound containing no urethane

bonds), reactive diluent, and photopolymerization initiator. The urethane (meth)acrylate is produced from a polyol such as a polyether diol, polyester polyol, and polycarbonate polyol, a diisocyanate, and a
5 hydroxyl group-containing (meth)acrylate.

Optical fiber cables in which optical fibers are enclosed are frequently installed underground or outdoors. Such optical fiber cables and glass fibers enclosed therein are apt to deteriorate
10 when underground water or rain invades the cables. To overcome such a problem, optical fiber coating materials having a low water absorption have been desired.

Moreover, the optical fibers manufacturing speed has been doubled in recent years due to a drastic
15 increase in the demand for optical fibers. Curable resin materials with low viscosity and a high curing speed have been used as the secondary coatings, ribbon matrix materials, or bundling materials for such
20 optical fibers to ensure high productivity of optical fibers.

An object of the present invention is to provide a photocurable resin composition with a low water absorption, low viscosity, and high curing speed.

25 Other objects and advantages of the present invention will become apparent from the following description of the invention.

Summary of the Invention

30 The above object and advantage can be achieved in the present invention by a photocurable

composition comprising a (meth)acrylate urethane compound derived at least in part from at least one fatty acid glyceride compound wherein said glyceride compound comprises on average at least 1.5 hydroxy groups.

The curable composition of the present invention may be formulated for use in a wide variety of applications including, for example, coatings and/or binders. In particular, these curable compositions offer relatively fast cure speeds which offer advantages in many application such as in the production of fiber optics wherein production speeds make it desirable to utilize primary coatings, secondary coatings (including, for example transparent and/or colored secondary coatings), inks, matrix materials and/or bundling materials that can be cured rapidly.

A method for forming the curable composition of the present invention comprising a process for forming the urethane compound by reacting

- (a) a fatty acid glyceride,
- (b) a polyisocyanate, and
- (c) a (meth)acrylate containing a hydroxyl group,

wherein the process includes (i) reacting the glyceride, the polyisocyanate, and the hydroxyl group-containing (meth)acrylate altogether; (ii) reacting the glyceride and the polyisocyanate, and reacting the resulting product with the hydroxyl group-containing (meth)acrylate; (iii) reacting the polyisocyanate and the hydroxyl group-containing (meth)acrylate, and reacting the resulting product with the glyceride; and

(iv) reacting the polyisocyanate and the hydroxyl group-containing (meth)acrylate, reacting the resulting product with the glyceride, and reacting the hydroxyl group-containing (meth)acrylate once more.

5

Detailed Description of Preferred Embodiments

(Meth)acrylic as used herein is understood to represent separately and collectively acrylic, methacrylic and mixtures thereof. Similarly,

10 (meth)acrylate as used herein is understood to represent separately and collectively acrylate, (meth)acrylate, and mixtures thereof.

Many conventional photocurable compositions for optical fiber coatings comprise a urethane
15 (meth)acrylate. Conventional urethane (meth)acrylate compounds may be manufactured from a polyol compound (such as a polyether diol, polyester polyol, or polycarbonate polyol), a diisocyanate compound, and a (meth)acrylate containing a hydroxyl group (hereinafter
20 called a hydroxyl group-containing (meth)acrylate).

The urethane (meth)acrylate of the present invention is prepared from a fatty acid glyceride compound wherein said glyceride compound comprises at least on average at least 1.5 hydroxy groups,
25 preferably from 2 to 8, and more preferably from 2 to 5 hydroxy groups. In addition, the preferred urethane (meth)acrylate compounds of the present invention include between 1 and 8 ethylenically unsaturated groups, more preferably between 2 and 5, and most
30 preferred between 2.5 and 3 of such groups.

The urethane (meth)acrylate compound of the

present invention is prepared by reacting a fatty acid
glyceride, such as, for example, a 12-hydroxystearic
acid triglyceride, a diisocyanate, and a hydroxyl group
containing (meth)acrylate. This reaction comprises the
5 reaction of at least one of the isocyanate groups on a
diisocyanate compound and a hydroxyl group of the 12-
hydroxystearic acid triglyceride and the reaction of an
isocyanate group of the diisocyanate compound and a
hydroxyl group of the hydroxyl group-containing
10 (meth)acrylate compound. The reaction product is a
polyfunctional compound having a structure in which the
residue of the 12-hydroxystearic acid triglyceride is
linked via a urethane group with at least one group-
containing (meth)acrylate. Specifically, such a
15 compound has a structure in which part or all of
hydroxyl groups of the 12-hydroxystearic acid
triglyceride are substituted by a urethane
(meth)acrylate group with a structure of the following
formula (1):

20



wherein R^1 is a residual group of the diisocyanate
compound from which two isocyanate groups are removed
25 and R^2 is a residual group of the hydroxyl group-
containing (meth)acrylate compound from which hydroxyl
groups are removed.


Examples of processes for reacting these
compounds include reacting the glyceride, diisocyanate,
30 and hydroxyl group-containing (meth)acrylate
altogether; reacting the glyceride and diisocyanate

first, and then reacting the resulting product with the hydroxyl group-containing (meth)acrylate; reacting diisocyanate and hydroxyl group containing (meth)acrylate first and then reacting the resulting
 5 product with glyceride; and the like can be given.

The glyceride preferably includes fatty acid glycerides, in particular, glycerides of fatty acids such as stearic acid, linolic acid, oleic acid, palmitic acid, ricinolic acid and/or mixtures thereof.
 10 Preferred fatty acid glycerides include those comprising three fatty acid moieties (i.e., moieties derived from fatty acid groups). The preferred glycerides include those that have been hydrogenated, in particular, those that have been hydrogenated to a
 15 hydrogenation rate of 20% or more, preferably 50% or more, more preferably 80% or more, and ideally 90% or more.

A preferred glyceride includes a glyceride represented by the following formula (2):

20



25

The (meth)acrylate urethane compound is preferably derived from a hydrogenated castor oil, comprising the at least one glyceride. Hydrogenated
 30 castor oil produced by hydrogenating castor oil is preferably used as the 12-hydroxystearic acid triglyceride.

Castor oil is an oil containing a glyceride

of ricinolic acid in an amount from about 87-91% and glycerides of other fatty acids such as linolic acid, oleic acid, and palmitic acid. A ricinolic acid glyceride, which is the major component, is a compound
5 having three hydroxyl groups. Hydrogenated castor oil is prepared by hydrogenating the castor oil to decrease the unsaturated double bonds contained therein. The hydrogenated castor oil is commercially available under the trademarks, for example, Castor Wax, Castor Wax B
10 (manufactured by Itoh Oil Manufacturing Co., Ltd.), Hydrogenated Castor, Hydrogenated Castor B, K-3-Wax, K-3-Wax-500 (manufactured by Kawaken Fine Chemicals Co. Ltd.), and Castor Wax A (manufactured by Nippon Oil and Fats Co., Ltd.). The 12-hydroxystearic acid
15 triglyceride used in the present invention is hydrogenated castor oil with a hydrogenation rate of 20% or more, preferably 50% or more, more preferably 80% or more, and ideally 90% or more. Too small a hydrogenation rate is not desirable because the
20 resulting composition of the present invention exhibits only a low curing speed.


The proportion of the glyceride, diisocyanate, and hydroxyl group-containing (meth)acrylate used in the preparation of the urethane
25 (meth)acrylate containing glyceride residues is determined so that for one mol of the hydroxyl group included in the glyceride, 0.2 to 3 mols, preferably 1 to 2 mols, of isocyanate group included in the diisocyanate compound and 0.2 to 1.5 mols, preferably
30 0.5 to 1 mol, of the hydroxyl group included in the hydroxyl group-containing (meth)acrylate compounds are

used.


Given as examples of the diisocyanate compounds used for the preparation of the urethane (meth)acrylate containing the 12-hydroxystearic acid triglyceride or hydrogenated castor oil as a raw material are 2,4-tolylene diisocyanate, 2,6-tolylene diisocyanate, 1,3-xylylene diisocyanate, 1,4-xylylene diisocyanate, 1,5-naphthalene diisocyanate, m-phenylene diisocyanate, p-phenylene diisocyanate, 3,3'-dimethyl-4,4'-diphenylmethane diisocyanate, 4,4'-diphenylmethane diisocyanate, 3,3'-dimethylphenylene diisocyanate, 4,4'-biphenylene diisocyanate, 1,6-hexane diisocyanate, isophorone diisocyanate, methylenebis(4-cyclohexyl isocyanate), 2,2,4-trimethylhexamethylene diisocyanate, bis(2-isocyanatethyl)fumarate, 6-isopropyl-1,3-phenyl diisocyanate, 4-diphenylpropane diisocyanate, lysine diisocyanate, hydrogenated diphenylmethane diisocyanate, hydrogenated xylylene diisocyanate, and tetramethylxylylene diisocyanate. Of these, 2,4-tolylene diisocyanate, isophorone diisocyanate, xylylene diisocyanate, methylene bis(4-cyclohexyl isocyanate), and the like are desirable. These diisocyanate compounds may be used either individually or in combinations of two or more.

The following compounds can be given as examples of the hydroxyl group-containing (meth)acrylate compound used for the preparation of the urethane (meth)acrylate comprising the 12-hydroxystearic acid triglyceride or hydrogenated castor oil as a raw material: 2-

hydroxyethyl (meth)acrylate, 2-
hydroxypropyl (meth)acrylate, 2-
hydroxybutyl (meth)acrylate, 2-hydroxy-3-
phenyloxypropyl (meth)acrylate, 1,4-butanediol
5 mono(meth)acrylate, 2-hydroxyalkyl (meth)acryloyl
phosphate, 4-hydroxycyclohexyl (meth)acrylate, 1,6-
hexanediol mono(meth)acrylate, neopentyl glycol
mono(meth)acrylate, trimethylolpropane
di(meth)acrylate, trimethylolethane di(meth)acrylate,
10 pentaerythritol tri(meth)acrylate, dipentaerythritol
penta(meth)acrylate, (meth)acrylate compounds shown by
the following formula (3) or (4),



15



wherein R_3 is a hydrogen atom or methyl group and n
indicates an integer from 1 to 15, and the compounds
20 obtained by the addition reaction of a glycidyl group-
containing compound (e.g. alkyl glycidyl ether, allyl
glycidyl ether, and glycidyl (meth)acrylate) and
(meth)acrylic acid. Of these hydroxyl group-containing
(meth)acrylates, 2-hydroxyethyl (meth)acrylate, 2-
25 hydroxypropyl (meth)acrylate, and the like are
especially desirable.

These hydroxyl group-containing
(meth)acrylate compounds may be used either
individually or in combinations of two or more.

30 The proportion of the hydrogenated castor
oil, diisocyanate, and hydroxyl group-containing

(meth)acrylate used in the preparation of the urethane (meth)acrylate containing hydrogenated castor oil is determined so that for one mol of the hydroxyl group included in the hydrogenated castor oil, 0.2 to 3 mols, preferably 1 to 2 mols, of isocyanate group included in the diisocyanate compound and 0.2 to 1.5 mols, preferably 0.5 to 1 mol, of the hydroxyl group included in the hydroxyl group-containing (meth)acrylate compounds are used.

10 In the above reactions, a urethanization catalyst such as copper naphthenate, cobalt naphthenate, zinc naphthenate, di-n-butyltin dilaurate, triethylamine, 1,4-diazabicyclo[2.2.2]octane, and 2,6,7-trimethyl-1,4-diazabicyclo[2.2.2]octane is
15 preferably used in an amount from 0.01 to 1 part by weight for 100 parts by weight of the total amount of the reactants. The reaction is carried out at a temperature from 10 to 90°C, and preferably 30 to 80°C, usually for 2 to 10 hours. The reaction is carried out
20 preferably in the presence of a reactive diluent which is described later in this specification.

The urethane (meth)acrylate derived from a glyceride is used in the composition of the present invention in an amount from 10 to 90 wt%, and
25 preferably from 20 to 80 wt%. If the amount of the urethane (meth)acrylate is less than 10 wt%, the water absorption of the cured products increases; if more than 90 wt%, the viscosity of the composition increases, whereby coatability of the composition is
30 impaired and decrease in the productivity of optical fibers may result.

(Meth)acrylate monomer

It is desirable to add (meth)acrylate monomers to the composition of the present invention. Such (meth)acrylate monomers may be monofunctional monomers, bifunctional monomers, or polyfunctional monomers.

Given as examples of the monofunctional monomers of (meth)acrylate are alicyclic (meth)acrylates such as isobornyl (meth)acrylate, bornyl (meth)acrylate, tricyclodecanyl (meth)acrylate, dicyclopentanyl (meth)acrylate, dicyclopentenyl (meth)acrylate, and cyclohexyl (meth)acrylate; benzyl (meth)acrylate, 4-butylcyclohexyl (meth)acrylate, (meth)acryloylmorpholine, 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, 2-hydroxybutyl (meth)acrylate, methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, isopropyl (meth)acrylate, butyl (meth)acrylate, amyl (meth)acrylate, isobutyl (meth)acrylate, t-butyl (meth)acrylate, pentyl (meth)acrylate, isoamyl (meth)acrylate, hexyl (meth)acrylate, heptyl (meth)acrylate, octyl (meth)acrylate, iso-octyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, nonyl (meth)acrylate, decyl (meth)acrylate, isodecyl (meth)acrylate, undecyl (meth)acrylate, dodecyl (meth)acrylate, lauryl (meth)acrylate, stearyl (meth)acrylate, iso-stearyl (meth)acrylate, tetrahydrofurfuryl (meth)acrylate, butoxyethyl (meth)acrylate, ethoxydiethylene glycol (meth)acrylate, polyoxyethylenenonyl phenyl ether

acrylate, phenoxyethyl(meth)acrylate, polyethylene glycol mono(meth)acrylate, polypropylene glycol mono(meth)acrylate, methoxyethylene glycol (meth)acrylate, ethoxyethyl (meth)acrylate, 5 methoxypolyethylene glycol (meth)acrylate, methoxypolypropylene glycol (meth)acrylate, dimethylaminoethyl(meth)acrylate, diethylaminoethyl (meth)acrylate, 7-amino-3,7-dimethyloctyl(meth)acrylate, (meth)acrylates having a 10 polyether skeleton of the following formula (5),



wherein R^4 is a hydrogen atom or methyl group, R^5 is an 15 alkylene group having 2-6, preferably 2-4, carbon atoms, R^6 represents a hydrogen atom or an alkyl group having 1-12, preferably 1-9, carbon atoms, and m is an integer from 0 to 12, preferably from 1 to 8.

As examples of commercially available 20 products of these monofunctional monomers, Aronix M-111, M-113, M-114, M-117 (manufactured by Toagosei Co., Ltd.), KAYARAD TC110S, R629, R644 (manufactured by Nippon Kayaku Co., Ltd.), IBXA (manufactured by Osaka Organic Chemical Industry Co., Ltd.), and the like can 25 be given.

Of the above monofunctional monomers, isobornyl (meth)acrylate and polyoxyethylene nonylphenyl ether acrylate are desirable.

Given as examples of bifunctional monomers 30 are ethylene glycol di(meth)acrylate, tetraethylene glycol di(meth)acrylate, polyethylene glycol

di(meth)acrylate, 1,4-butanediol di(meth)acrylate, 1,6-hexanediol di(meth)acrylate, neopentyl glycol di(meth)acrylate, tris(2-hydroxyethyl)isocyanurate di(meth)acrylate, tricyclodecanedimethanol

5 di(meth)acrylate, di(meth)acrylate of alkylene oxide addition diol of bisphenol A, di(meth)acrylate of alkylene oxide addition diol of hydrogenated bisphenol A, epoxy(meth)acrylate prepared by the addition of (meth)acrylate to diglycidyl ether of bisphenol A, and

10 the like.

As examples of commercially available products of these bi-functional monomers, Yupimer UV, SA1002 (manufactured by Mitsubishi Chemical Corp.), Viscoat 700 (manufactured by Osaka Organic Chemical

15 Industry Co., Ltd.), KAYARAD R-604, HX-620 (manufactured by Nippon Kayaku Co., Ltd.), Aronix M-210, M-215 (manufactured by Toagosei Co., Ltd.), and the like can be given.

Of the above bifunctional monomers,

20 tricyclodecanedimethanol diacrylate and di(meth)acrylate of alkylene oxide addition diol of bisphenol A are particularly preferred.

As examples of polyfunctional monomers, trimethylolpropane tri(meth)acrylate, ethoxylated

25 trimethylolpropane tri(meth)acrylate, propoxylated trimethylolpropane tri(meth)acrylate, pentaerythritol tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, dipentaerythritol hexa(meth)acrylate,

ditrimethylolpropane tetra(meth)acrylate,

30 dipentaerythritolmonohydroxy penta(meth)acrylate, and the like can be given.

These polyfunctional monomers can be commercially available under the trademarks, for example, FA731A (manufactured by Hitachi Chemical Industries Co., Ltd.), Aronix M-315, M-350, M-360, M-405, M-450 (manufactured by Toagosei Co., Ltd.), KAYARAD DPHA, D-310, D-320, D-330, DPCA-20, DPCA-30, DPCA-60, DPCA-120 (manufactured by Nippon Kayaku Co., Ltd.), Viscoat #400 (manufactured by Osaka Organic Chemical Industry Co., Ltd.), and Photomer 4172, 4149 (manufactured by SAN NOPCO, Ltd.). Of these, Aronix M-450, Viscoat #400, and Photomer 4149 are particularly preferred.

The (meth)acrylate monomers affect viscosity of the composition and properties of the cured products and act as a solvent or a reactive diluent during the synthesis of the urethane (meth)acrylates. These reactive diluents may be used either individually or in combinations of two or more, and are usually added in an amount from 3 to 70 wt%, and preferably from 10 to 50 wt%, of the composition of the present invention. The use of the reactive diluents in this range ensures excellent coatability and curing speed of the composition, high toughness of the cured products, while minimizing the cure shrinkage rate.

N-vinyl group-containing monomer

It is desirable to add monomers containing an N-vinyl group (hereinafter called "N-vinyl group-containing monomers") to the composition of the present invention. The N-vinyl group-containing monomers not only act as reactive diluents, but also increase the

curing speed of the composition, if added in an appropriate amount. As examples of the monomers containing an N-vinyl group, N-vinylpyrrolidone, N-vinylcaprolactam, N-vinylformamide, N-vinylcarbazole, and the like can be given. The amount of the compound containing N-vinyl group is determined so that the amount of the N-vinyl group in the compound is two mols or less, preferably from 0.2 to 1 mol, for one mol of the (meth)acryloyl group contained in the composition. If the amount of the N-vinyl group is more than two mols, the curing speed of the composition decreases.

Other urethane (meth)acrylates

The composition of the present invention may contain urethane (meth)acrylates other than the urethane (meth)acrylate prepared using 12-hydroxystearic acid triglyceride or hydrogenated castor oil as a raw material.

Conventionally known urethane acrylates prepared by reacting a hydroxyl group-containing (meth)acrylate and a polyisocyanate or reacting a hydroxyl group-containing (meth)acrylate, polyisocyanate, and polyol, for example, can be used as such a urethane (meth)acrylate.

Given as examples of the urethane acrylate obtained by the reaction of a hydroxyl group-containing (meth)acrylate and a polyisocyanate are a reaction product of hydroxyethyl(meth)acrylate and 2,5- or 2,6-bis(isocyanatemethyl)-bicyclo[2.2.1]heptane, a reaction product of hydroxyethyl(meth)acrylate and 2,4-tolylene diisocyanate, a reaction product of

hydroxyethyl(meth)acrylate and isophorone diisocyanate,
a reaction product of hydroxypropyl (meth)acrylate and
2,4-tolylene diisocyanate, and a reaction product of
hydroxypropyl(meth)acrylate and isophorone
5 diisocyanate.

A polyether diol, polyester diol,
polycarbonate diol, polycaprolactone diol, and the like
can be given as the polyol used for preparing the
urethane acrylate by the reaction of a hydroxyl group-
10 containing (meth)acrylate, polyisocyanate, and polyol.
The polyether diol includes aliphatic polyether diols,
alicyclic diols, and aromatic diols. These polyols may
be used either individually or in combinations of two
or more. It is also possible to use a polyols with two
15 or more valence obtained by the reaction of a diol and
a polyisocyanate as the polyol. There are no specific
limitations to the manner of polymerization of each
structural unit in these polyols. Any one of random
polymerization, block polymerization, and graft
20 polymerization is acceptable.

As examples of the aliphatic polyether
diol, polyethylene glycol, polypropylene glycol,
polytetramethylene glycol, polyhexamethylene glycol,
polyheptamethylene glycol, polydecamethylene glycol,
25 and polyether diols produced by ring-opening
copolymerization of two or more ion-polymerizable
cyclic compounds can be given.

Given as examples of such ion-polymerizable
cyclic compounds are cyclic ethers such as ethylene
30 oxide, propylene oxide, butene-1-oxide, isobutene
oxide,

3,3-bis(chloromethyl)oxetane, tetrahydrofuran,
2-methyltetrahydrofuran, 3-methyltetrahydrofuran,
dioxane, trioxane, tetraoxane, cyclohexene oxide,
styrene oxide, epichlorohydrin, glycidyl methacrylate,
5 allyl glycidyl ether, allyl glycidyl carbonate,
butadiene monoxide, isoprene monoxide, vinyloxetane,
vinyltetrahydrofuran, vinylcyclohexene oxide, phenyl
glycidyl ether, butyl glycidyl ether, and glycidyl
benzoate.

10 Given as specific examples of polyether
diols produced by the ring-opening copolymerization of
ion-polymerizable cyclic compounds are binary
copolymers produced by the combinations of, for
example, tetrahydrofuran and propylene oxide,
15 tetrahydrofuran and 2-methyl tetrahydrofuran,
tetrahydrofuran and 3-methyl tetrahydrofuran,
tetrahydrofuran and ethylene oxide, propylene oxide and
ethylene oxide, and butene-1-oxide and ethylene oxide;
and ternary copolymers produced by the combination of,
20 for example, tetrahydrofuran, butene-1-oxide, and
ethylene oxide.

 A polyether diol obtained by the ring-
opening copolymerization of the above-mentioned ion-
polymerizable cyclic compound and a cyclic imine such
25 as ethyleneimine, a cyclic lactone acid such as β -
propylactone and glycolic acid lactide, or a
dimethylcyclopolsiloxane can also be used.

 These aliphatic polyether diols are also
commercially available under the trademarks, for
30 example, PTMG 650, PTMG 1000, PTMG 2000 (manufactured
by Mitsubishi Chemical Corp.), PPG400, PPG1000,

EXCENOL720, 1020, 2020 (manufactured by Asahi Oline Co., Ltd.), PEG1000, Unisafe DC 1100, DC 1800 (manufactured by Nippon Oil and Fats Co., Ltd.), PPTG2000, PPTG1000, PTG400, PTGL2000 (manufactured by
5 Hodogaya Chemical Co., Ltd.), and Z-3001-4, Z-3001-5, PBG2000A, PBG2000B, EO/BO4000, EO/BO2000 (manufactured by Daiichi Kogyo Seiyaku Co., Ltd.).

As examples of the alicyclic polyether diol, alkylene oxide addition diol of hydrogenated
10 bisphenol A, alkylene oxide addition diol of hydrogenated bisphenol F, and alkylene oxide addition diol of 1,4-cyclohexane diol can be given.

As examples of the aromatic polyether diol, alkylene oxide addition diol of bisphenol A, alkylene
15 oxide addition diol of bisphenol F, alkylene oxide addition diol of hydroquinone, alkylene oxide addition diol of naphthohydroquinone, and alkylene oxide addition diol of anthrahydroquinone can be given. These aromatic polyether diols can be commercially available
20 under the trademarks, for example, Uniol DA400, DA700, DA1000, and DA4000 (manufactured by Nippon Oil and Fats Co., Ltd.).

As the polyester diol, polyester diols prepared by the reaction of a polyhydric alcohol and a
25 polybasic acid can be given. Here, given as examples of the polyhydric alcohol are ethylene glycol, polyethylene glycol, propylene glycol, polypropylene glycol, tetramethylene glycol, polytetramethylene glycol, 1,6-hexanediol, neopentyl glycol, 1,4-
30 cyclohexanedimethanol, 3-methyl-1,5-pentane diol, 1,9-nonane diol, and 2-methyl-1,8-octane diol. As example

of the polybasic acid, phthalic acid, isophthalic acid, terephthalic acid, maleic acid, fumaric acid, adipic acid, sebacic acid, and the like can be given. As examples of commercially available products of

5 polyester diols, Kurapol P-2010, P-1010, L-2010, L-1010, A-2010, A-1010, F-2020, F-1010, PMIPA-2000, PKA-A, PNOA-2010, PNOA-1010 (manufactured by Kuraray Co., Ltd.), and the like can be given.

As the polycarbonate diol, polycarbonate of

10 polytetrahydrofuran, polycarbonate of 1,6-hexanediol, and the like can be given. Commercially available products of the polycarbonate diol include DN-980, 981, 982, 983 (manufactured by Nippon Polyurethane Industry Co., Ltd.), PC-8000 (manufactured by PPG), PC-THF-CD

15 (manufactured by BASF), and the like.

As the polycaprolactone diol,

polycaprolactone diols prepared by reacting ϵ -caprolactone and a diol can be given as examples. As the diol used in this reaction, ethylene glycol,

20 polyethylene glycol, propylene glycol, polypropylene glycol, tetramethylene glycol, polytetramethylene glycol, 1,2-polybutylene glycol, 1,6-hexanediol, neopentyl glycol, 1,4-cyclohexanedimethanol, 1,4-butanediol, and the like can be given. These

25 polycaprolactone diols are also commercially available under the trademarks, for example, PLACCEL 205, 205AL, 212, 212AL, 220, and 220AL (manufactured by Daicel Chemical Industries, Ltd.).

Other polyols which can be used include,

30 for example, ethylene glycol, propylene glycol, 1,4-butanediol, 1,5-pentane diol, 1,6-hexanediol, neopentyl

glycol, 1,4-cyclohexanedimethanol, hydrogenated bisphenol A, hydrogenated bisphenol F, dimethylol compound of dicyclopentadiene, tricyclodecanedimethanol, pentacyclodecanedimethanol, 5 β -methyl- δ -valerolactone, polybutadiene with a terminal hydroxy group, hydrogenated polybutadiene with a terminal hydroxy group, polydimethylsiloxane with a diol terminal, and polydimethylsiloxane carbitol-modified polyol.

10 Among the above polyether polyols, polyester polyols, polycarbonate polyols, and polycaprolactone polyols, polyether polyols are desirable, because polyether polyols can produce polyurethanes with excellent durability and superior 15 low temperature characteristics.

The following compounds can be given as examples of the diisocyanates used in the present invention: 2,4-tolylene diisocyanate, 2,6-tolylene diisocyanate, 1,3-xylylene diisocyanate, 1,4-xylylene 20 diisocyanate, 1,5-naphthalene diisocyanate, m-phenylene diisocyanate, p-phenylene diisocyanate, 3,3'-dimethyl-4,4'-diphenylmethane diisocyanate, 4,4'-diphenylmethane diisocyanate, 3,3'-dimethylphenylene diisocyanate, 4,4'-biphenylene diisocyanate, 1,6-hexane diisocyanate, 25 isophorone diisocyanate, methylenebis(4-cyclohexylisocyanate), 2,2,4-trimethylhexamethylene diisocyanate, bis(2-isocyanatethyl) fumarate, 6-isopropyl-1,3-phenyl diisocyanate, 4-diphenylpropane diisocyanate, lysine diisocyanate, hydrogenated 30 diphenylmethane diisocyanate, hydrogenated xylylene diisocyanate, and tetramethylxylylene diisocyanate. Of

these, 2,4-tolylene diisocyanate, isophorone diisocyanate, xylylene diisocyanate, methylenebis(4-cyclohexylisocyanate), and the like are preferable. These diisocyanates may be used either individually or
5 in combinations of two or more.

The following compounds can be given as examples of the hydroxyl group containing (meth)acrylates used in the present invention: 2-hydroxyethyl(meth)acrylate, 2-
10 hydroxypropyl(meth)acrylate, 2-hydroxybutyl(meth)acrylate, 2-hydroxy-3-phenyloxypropyl(meth)acrylate, 1,4-butanediol mono(meth)acrylate, 2-hydroxyalkyl(meth)acryloyl phosphate, 4-hydroxycyclohexyl(meth)acrylate, 1,6-
15 hexanediol mono(meth)acrylate, neopentyl glycol mono(meth)acrylate, trimethylolpropane di(meth)acrylate, trimethylolethane di(meth)acrylate, pentaerythritol tri(meth)acrylate, dipentaerythritol penta(meth)acrylate, and (meth)acrylates shown by the
20 above-mentioned formula (2) or (3). Of these hydroxyl group-containing (meth)acrylates, 2-hydroxyethyl(meth)acrylate, 2-hydroxypropyl(meth)acrylate, and the like are particularly preferred. In addition to these(meth)acrylates, compounds obtained by the
25 addition reaction of a glycidyl group-containing compound such as an alkyl glycidyl ether, aryl glycidyl ether, or glycidyl(meth)acrylate and (meth)acrylic acid can also be used as the hydroxyl group-containing (meth)acrylate.

30 These hydroxyl group-containing (meth)acrylates may be used either individually or in

combinations of two or more.

These urethane (meth)acrylates can be synthesized simultaneously as a mixture with the above-mentioned urethane (meth)acrylates which are prepared
5 using hydrogenated castor oil as a raw material.

The proportion of the urethane (meth)acrylates prepared using hydrogenated castor oil as a raw material and the other urethane (meth)acrylates used in the composition of the present
10 invention should preferably be determined so that the ratio P of the following formula (6) is from 0 to 0.7, and preferably from 0 to 0.6.

$$P = B / (A+B) \quad (6)$$

15

wherein A is the amount (weight) of the urethane (meth)acrylates prepared using hydrogenated castor oil as a raw material and B is the amount (weight) of the other urethane (meth)acrylates. If P is more than 0.7,
20 the cured products produced from the composition of the present invention exhibit increased water absorption.

The composition of the present invention can be cured by radiation. A photo-polymerization initiator can be used, if necessary. Here, radiation
25 includes infrared radiation, visible rays, ultraviolet radiation, X-rays, electron beams, α -rays, β -rays, γ -rays, and the like.

Given as examples of photo-polymerization initiators which can be used in the present invention
30 are 1-hydroxycyclohexyl phenyl ketone, 2,2-dimethoxy-2-phenylacetophenone, xanthone, fluorenone, benzaldehyde,

fluorene, anthraquinone, triphenylamine, carbazole, 3-methylacetophenone, 4-chlorobenzophenone, 4,4'-dimethoxybenzophenone, 4,4'-diaminobenzophenone, Michler's ketone, benzoin propyl ether, benzoin ethyl ether, benzyl dimethyl ketal, 1-(4-isopropylphenyl)-2-hydroxy-2-methylpropan-1-one, 2-hydroxy-2-methyl-1-phenylpropan-1-one, thioxanethone, diethylthioxanthone, 2-isopropylthioxanthone, 2-chlorothioxanthone, 2-methyl-1-[4-(methylthio)phenyl]-2-morpholino-propan-1-one, 2,4,6-trimethylbenzoyldiphenylphosphine oxide, bis-(2,6-dimethoxybenzoyl)-2,4,4-trimethylpentylphosphine oxide, and the like.

As commercially available products of photo-polymerization initiators, Irgacure 184, 369, 651, 500, 819, 907, CGI1700, CGI1750, CGI1850, CG24-61 (manufactured by Ciba Specialty Chemicals Co., Ltd.), Lucirin LR8728 (manufactured by BASF), Darocur 1116, 1173 (manufactured by Ciba Specialty Chemicals Co., Ltd.), Ubecryl P36 (manufactured by UCB), and the like can be given. Of these, Irgacure 184, Irgacure 651, Irgacure 907, Darocur 1173, and Lucirin LR 8728 are particularly preferred.

The amount of the photo-polymerization initiators used in the composition of the present invention is in the range from 0.1 to 10 wt%, and preferably from 0.5 to 7 wt%.

Other components

Components other than the above-described components may be added to the composition of the present invention as required, inasmuch as the

characteristics of the composition of the present invention are not adversely affected.

For instance, an amine compound may be added to the composition of the present invention to
5 suppress generation of hydrogen gas which causes transmission loss of optical fibers. As such an amine compound, diallylamine, diisopropylamine, diethylamine, diethylhexylamine, and the like can be given.

Other additives which can be added in
10 addition to the above-mentioned components include antioxidants, UV absorbers, light stabilizers, silane coupling agents, heat polymerization inhibitors, leveling agents, surfactants, preservatives, plasticizers, lubricants, coloring matters, solvents,
15 fillers, aging preventives, wettability improvers, coating surface improvers, and the like.

As examples of antioxidants, Irganox 1010, 1035, 1076, 1222 (manufactured by Ciba Specialty Chemicals, Co., Ltd.), Antigen P, 3C, FR, GA-80
20 (manufactured by Sumitomo Chemical Industries Co., Ltd.), and the like can be given. As UV absorbers, Tinuvin P, 234, 320, 326, 327, 328, 329, 213 (manufactured by Ciba Specialty Chemicals Co., Ltd.), Seesorb 102, 103, 501, 202, 712, 704 (manufactured by
25 Sypro Chemical Co., Ltd.), and the like can be given. As silane coupling agents, γ -aminopropyltriethoxysilane, γ -mercaptopropyltrimethoxysilane, γ -methacryloxy-propyltrimethoxysilane, and commercially available products such as SH6062, SH6030 (manufactured
30 by Toray-Dow Silicone Co., Ltd.), KBE903, 603, 403 (manufactured by Shin-Etsu Chemical Co., Ltd.), and the

like can be given.

The composition of the present invention has a viscosity of preferably in the range from 200 to 20,000 cp, and more preferably from 1,000 to 16,000 cp, at 25°C. When the composition is used as a coating material for optical fibers, the use of the composition with a viscosity of more than 20,000 cp or less than 200 cp impairs coatability, which results in a decrease in the productivity of optical fibers.

Preferred composition include those wherein the cure speed, as measured by the ratio of Young's modulus of elasticity as described below) is greater than 0.10, and more preferably 20 or greater. If a N-vinyl monomer is present in the composition, the cure speed is preferably at least 20 and more preferably 30 or greater.

The radiation-curable compositions of the present invention may be formulated such that the composition after cure has a tensile modulus as low as 0.1 MPa and as high as 2,000 MPa or more. Those having a modulus in the lower range, for instance, from 0.1 to 10 MPa, preferably 0.1 to 5 MPa, and more preferably 0.5 to less than 3 MPa are typically suitable for inner primary coatings for fiber optics. In contrast, suitable compositions for outer primary coatings, inks and matrix materials generally have a modulus of above 50 MPa, with outer primary coatings tending to have a modulus more particularly above 100 up to 1,000 MPa and matrix materials tending to be more particularly between about 50 MPa to about 500 MPa.

Elongation and tensile strength of these materials can also be optimized depending on the design criteria for a particular use. For cured coatings formed

from radiation-curable compositions formulated for use as inner primary coatings on optical fibers, the elongation-at-break is typically greater than 80%, more preferably the elongation-at-break is at least 110%, more preferably at least 150% but not typically higher than 400%. For coatings formulated for outer primary coatings, inks and matrix materials the elongation-at-break is typically between 10% and 100%, and preferably higher than 20%.

10 The glass transition temperature (T_g), measured as the peak tan-delta determined by dynamic mechanical analysis (DMA), can be optimized depending on the particulars of the application. The glass transition temperature may be from 10°C down to -70°C
15 or lower, more preferably lower than -10°C for compositions formulated for use as inner primary coatings and 10°C to 120°C or higher, more preferably above 30°C, for compositions designed for use as outer primary coatings, inks and matrix materials.

20 The composition of the present invention will preferably have a cure speed of 1.0 J/cm² or less (at 95% of maximum attainable modulus). For an inner, outer primary coating, ink or matrix material, cure speed is preferably about 0.5 J/cm² or less (at 95% of
25 maximum attainable modulus), and more preferably, about 0.3 J/cm² or less, and even more preferably, about 0.2 J/cm² or less.

 The cured products obtained by the polymerization of the resin composition of the present
30 invention are particularly suitable for use as a coating material for optical fibers, optical fiber ribbons, and the like including primary coatings, secondary coatings, colored secondary coatings, inks,

matrix materials and bundling materials.

Examples

The present invention will be explained in
5 more detail by way of examples, which are not intended
to be limiting of the present invention.

Example 1

A reaction vessel equipped with a stirrer
10 was charged with 190 g of 2,4-tolylene diisocyanate,
0.17 g of 2,6-di- t-butyl-4-methylphenol as a
polymerization inhibitor, 0.06 g of phenothiazine, 0.56
g of dibutyltin dilaurate, and 145 g isobornyl
acrylate. After cooling the mixture with ice to 12°C,
15 127 g of 2-hydroxyethyl acrylate was added while
maintaining the temperature at 25 to 30°C. After
stirring for a further one hour at 23°C, 383 g of
hydrogenated castor oil with a hydroxyl value of 159.5
(mg-KOH/g) and an iodine value of 2.1 (g I₂/100 g)
20 (Caster Wax B, manufactured by Itoh Oil Chemicals Co.,
Ltd.) was added. The mixture was stirred for 6 hours at
70°C before terminating the reaction. Then, 122 g of N-
vinylpyrrolidone, 30 g of Irgacure 651 (a photo-
polymerization initiator), and 3 g of Irganox 1035 (an
25 antioxidant) were added to the resulting product. The
mixture was stirred for two hours at 55°C to obtain
1,000 g of the composition of the present invention.

The hydrogenation rate of the hydrogenated
castor oil used was calculated to be 97.5-97.6% by
30 applying the known iodine value of castor oil (83-89 g
I₂/100 g) to the following formula.

Hydrogenation rate (%) = (1 - iodine value of hydrogenated castor oil/ iodine value of castor oil)X100

5

Example 2

1,000g of the composition of the present invention was prepared in the same manner as in Example 1, except that the amount of isobornyl acrylate used was 94 g and that of N-vinylpyrrolidone was 173 g.

Example 3

1,000g of the composition of the present invention was prepared in the same manner as in Example 1, except the amount of isobornyl acrylate used was 207 g and that of N-vinylpyrrolidone was 60 g.

Example 4

1,000g of the composition of the present invention was prepared in the same manner as in Example 1, except that the amount of isobornyl acrylate used was 267 g and no N-vinylpyrrolidone was added.

Example 5

A reaction vessel equipped with a stirrer was charged with 172 g of 2,4-tolyene diisocyanate, 1.4 g of 2,6-di- t-butyl-4-methylphenol as a polymerization inhibitor, 0.5 g of phenothiazine, 0.43 g of dibutyltin dilaurate, and 145 g isobornyl acrylate. After cooling the mixture with ice to 12°C, 114.5 g of 2-hydroxyethyl acrylate was added while

maintaining the temperature below 30°C. After stirring for a further one hour at 23°C, 191.5 g of hydrogenated castor oil (Caster Wax B) and 220 g of tetramethylene glycol (PTMG 1000) were added. The mixture was stirred
5 for 6 hours at 70°C before terminating the reaction. Then, 122 g of N-vinylpyrrolidone, 30 g of Irgacure 651, and 3 g of Irganox 1035 were added to the resulting product. The mixture was stirred for two hours at 55°C to obtain 1,000 g of the composition of
10 the present invention.

Example 6

A reaction vessel equipped with a stirrer was charged with 190 g of 2,4-tolylene diisocyanate,
15 0.17 g of 2,6-di-t-butyl-4-methylphenol as a polymerization inhibitor, 0.06 g of phenothiazine, 0.56 g of dibutyltin dilaurate, and 145 g isobornyl acrylate as a reactive diluent. After cooling the mixture with ice to 12°C, 127 g of 2-hydroxyethyl acrylate was added
20 while maintaining the temperature at 25-30°C. After stirring for a further one hour at 23°C, 383 g of hydrogenated castor oil with a hydroxyl value of 160.3 (mg-KOH/g), an iodine value of 2.0 (g I₂/100 g), and a hydrogenation rate of 98% (Caster Wax, manufactured by
25 Itoh Oil Chemicals Co., Ltd.) was added. The mixture was stirred for 6 hours at 70°C before terminating the reaction. Then, 122 g of N-vinylpyrrolidone, 30 g of Irgacure 651 (a photo-polymerization initiator), and 3 g of Irganox 1035 (an antioxidant) were added to the
30 resulting product. The mixture was stirred for two

hours at 55°C to obtain 1,000 g of the composition of the present invention.

Comparative Example 1

5 A reaction vessel equipped with a stirrer was charged with 192 g of 2,4-tolylene diisocyanate, 0.17 g of 2,6-di-t-butyl-4-methylphenol as a polymerization inhibitor, 0.06 g of phenothiazine, 0.56 g of dibutyltin dilaurate, and 145 g isobornyl
10 acrylate. After cooling the mixture with ice to 12°C, 128 g of 2-hydroxyethyl acrylate was added while maintaining the temperature below 30°C. After stirring for a further one hour at 23°C, 380 g of castor oil with a hydroxyl value of 163.0 (mg-KOH/g) and an iodine
15 value of 85.7 (g I₂/100 g) (Caster Oil LAV, manufactured by Itoh Oil Chemicals Co., Ltd.) was added. The mixture was stirred for 6 hours at 70°C before terminating the reaction. Then, 122 g of N-vinylpyrrolidone, 30 g of Irgacure 651, and 3 g of Irganox 1035 were added to the
20 resulting product. The mixture was stirred for two hours at 55°C to obtain 1,000 g of a comparative composition.

Comparative Example 2

25 A reaction vessel equipped with a stirrer was charged with 154 g of 2,4-tolylene diisocyanate, 1.4 g of 2,6-di-t-butyl-4-methylphenol, 0.5 g of phenothiazine, 0.43 g of dibutyltin dilaurate, and 145 g isobornyl acrylate. After cooling the mixture with
30 ice to 12°C, 103 g of 2-hydroxyethyl acrylate was added

while maintaining the temperature below 30°C. After stirring for a further one hour at 23°C, 441 g of tetramethylene glycol (PTMG 1000) was added. The mixture was stirred for 6 hours at 70°C before
5 terminating the reaction. Then, 122 g of N-vinylpyrrolidone, 30 g of Irgacure 651, and 3 g of Irganox 1035 were added to the resulting product. The mixture was stirred for two hours at 55°C to obtain 1,000 g of a comparative composition.

10

Comparative Example 3

A reaction vessel equipped with a stirrer was charged with 217 g of 2,4-tolylene diisocyanate, 1.4 g of 2,6-di-t-butyl-4-methylphenol, 0.5 g of
15 phenothiazine, 0.43 g of dibutyltin dilaurate, and 145 g isobornyl acrylate. After cooling the mixture with ice to 12°C, 230 g of 2-hydroxyethyl acrylate was added while maintaining the temperature below 30°C. After stirring for a further one hour at 23°C, 253 g of
20 tetramethylene glycol (PTMG 1000) was added. The mixture was stirred for 6 hours at 70°C before terminating the reaction. Then, 122 g of N-vinylpyrrolidone, 30 g of Irgacure 651, and 3 g of Irganox 1035 were added to the resulting product. The
25 mixture was stirred for two hours at 55°C to obtain 1,000 g of a comparative composition.

Comparative Example 4

1,000g of a comparative composition was
30 prepared in the same manner as in Comparative Example

3, except that the amount of isobornyl acrylate used was 267 g and N-vinylpyrrolidone was not added.

Test Methods

5 The viscosity and curing speed of the compositions prepared in Examples 1-5 and Comparative Examples 1-4, and Young's modulus of elasticity and water absorption of the cured products produced from the compositions were measured according to the
10 following methods. The results are shown in Table 1.

Measurement of viscosity

 The viscosity was measured at 25°C using a B-type viscometer manufactured by Tokyo Keiki Co., Ltd.

15

Curing speed of the composition and properties of the cured products

1. Preparation of test specimens

 The photocurable resin composition was
20 applied on a glass plate using an applicator bar and irradiated with ultraviolet radiation at a dose of 0.01 J/cm² or 0.1 J/cm² using a UV curing system (jet printer HMW 312MX, manufactured by ORC Manufacturing Co., Ltd.) in an nitrogen atmosphere to produce cure films
25 with a thickness of 200 µm. The cured films were peeled from the glass plate and allowed to stand for 24 hours at a temperature of 23°C and a relative humidity of 50%, thereby obtaining a test specimen.

30 2. Measurement of Young's modulus of elasticity

 The test specimen was cut into strips with

a width of 6 mm to measure Young's modulus of elasticity at 23°C according to the JIS K7113 using an autograph AGS-1KND (manufactured by Shimazu Corporation), provided that the tensile velocity was 1
5 mm/min. The Young's modulus of elasticity was calculated from tensile stress at 2.5% distortion.

3. Calculation of curing speed

The ratio of Young's modulus of elasticity
10 of the film cured by 0.01 J/cm² UV irradiation and that of the film cured by 0.1 J/cm² UV irradiation was calculated. This ratio was taken as the curing speed.

4. Measurement of water absorption

15 The liquid curable resin composition was applied to a glass plate using an applicator bar with a thickness of 250 µm and cured with ultraviolet radiation at a dose of 1.0 J/cm² in the air. The cured product was conditioned for more than 12 hours at a
20 room temperature of 23°C and a relative humidity of 50%, and peeled off from the glass plate to obtain a test specimen. Water absorption of the cured product was measured according to the JIS K7209.

Table 1

	Example							Comparative Example			
	1	2	3	4	5	6		1	2	3	4
Urethane acrylate prepared using hydrogenated castor oil (Caster Wax B)	70	70	70	70	35	-		-	-	-	-
Urethane acrylate prepared using hydrogenated castor oil (Caster Wax)	-	-	-	-	-	70		-	-	-	-
Urethane acrylate prepared using castor oil (Caster oil LAV)	-	-	-	-	-	-		70	-	-	-
Polyether urethane acrylate	-	-	-	-	35			-	70	40	40
Urethane acrylate(bis(2-acryloxyethyl)-2,4-tolylene carbamate)	-	-	-	-	-	-		-	-	30	30
Isobornyl acrylate	14.5	9.4	20.7	26.7	14.5	14.5		14.5	14.5	14.5	26.7
N-vinylpyrrolidone	12.2	17.3	6.0	-	12.2	12.2		12.2	12.2	12.2	-
Irgacure 651	3.0	3.0	3.0	3.0	3.0	3.0		3.0	3.0	3.0	3.0

	Example						Comparative Example			
	1	2	3	4	5	6	1	2	3	4
Irganox 1035	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3
Viscosity at 25°C (cps)	7500	5000	8600	9800	8300	7400	7500	4400	15000	16000
Young's modulus (kg/mm ²)										
UV irradiation										
0.01 (J/cm ²): a	34	45	18	10	35	35	*N/C	3	8	5
0.1 (J/cm ²): b	92	89	86	86	93	92	22	14	87	70
Curing speed: a/b	0.37	0.50	0.20	0.12	0.38	0.38	-	0.21	0.09	0.07
Water absorption of cured product (%)	1.4	2.2	0.9	0.4	2.5	1.3	1.5	3.6	3.7	3.0

The viscosity of both the compositions in Examples and Comparative Examples was in the preferable range from 4,400 to 16,000 cp. The composition of the Comparative Example 1 was prepared in the same manner as in the composition of Example 1, except for using the urethane (meth)acrylate which was prepared using unhydrogenated castor oil. This comparative composition do not cure (*N/C) at the 0.01 (J/cm²) dose and exhibited only an extremely low photo-curing speed. The composition of the Comparative Examples 2, 3, and 4 were prepared using a conventional urethane (meth)acrylate instead of the urethane (meth)acrylate of the present invention prepared using hydrogenated castor oil. These compositions exhibited only a small curing speed and the cured products made from these compositions exhibited high water absorption. The composition of Example 2 exhibited low water absorption of 2.2 %, in spite of the large content (17.3 wt%) of N-vinylpyrrolidone which tends to increase water absorption. These experimental results demonstrate the effect of the photocurable resin composition of the present invention comprising the urethane (meth)acrylate which is prepared by using the hydrogenated castor oil as a raw material. In addition, the preferred composition are those wherein the water absorption of the cured composition is less than 3.0%, as measured by the method set forth below, more preferably 2.5% or less and when N-vinyl monomers are not present less than 1.0%, and preferably less than 0.5%.

Because the photocurable resin composition


of the present invention can be applied at a high speed due to its moderate viscosity and is photocurable at a high speed, the composition can exhibit high productivity when used as a coating material for

5 optical fibers. In addition, because the cured products is only slightly affected by water due to their small water absorption, the composition is an ideal coating material for optical fibers.

CLAIMS

What is claimed is:

- 5 1. A photocurable composition comprising a
(meth)acrylate urethane compound derived at least
in part from at least one fatty acid glyceride
compound wherein said glyceride compound comprises
at least on average at least 1.5 hydroxy groups.
- 10 2. The photocurable composition according to claim 1
wherein said fatty acid glyceride compound
comprises three fatty acid moieties.
3. The photocurable composition according to any one
of claims 1-2, wherein the (meth)acrylate urethane
15 compound has an ethylenic unsaturation between 2
and 5.
4. The photocurable composition according to any one
of claims 1-3 wherein the hydrogenation rate of
the fatty acid glyceride is at least 20% or more.
- 20 5. The photocurable composition according to any one
of claims 1-4 wherein the fatty acid includes a
stearic acid, linolic acid, oleic acid, palmatic
acid and/or ricinolic acid.
6. The photocurable composition according to any one
25 of claims 1-5 wherein the fatty acid glyceride
comprises 2-5 hydroxy groups.
7. The photocurable composition according to any one
of claims 1-6 wherein the at least one fatty acid
glyceride includes a glyceride represented by the
30 following formula (2):



- 5
8. The photocurable composition according to any one of claims 1-7 wherein the (meth)acrylate urethane compound is derived from a hydrogenated castor oil, comprising the at least one fatty acid
- 10 glyceride.
9. The photocurable composition according to any one of claims 1-7 wherein the (meth)acrylate urethane compound is a polyfunctional compound comprising at least two (meth)acrylate-containing groups
- 15 linked via a urethane group to a residue of the fatty acid glyceride.
10. The photocurable composition according to any one of claims 1-9 wherein the composition further comprises a monomer having an N-vinyl group.
- 20 11. An article comprising a cured composition according to any one of claims 1-10.
12. A curable fiber optic primary coating composition, secondary coating composition, colored secondary coating composition, matrix material composition,
- 25 or ink composition comprising the curable composition according to any of claims 1-10.
13. A process for forming the curable composition according to any one of claims 1-10 comprising forming the (meth)acrylate urethane compound by
- 30 reacting the at least one fatty acid glyceride with a diisocyanate and a (meth)acrylate containing a hydroxyl group.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 99/00423

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G18/81 C08G18/67 C09D175/16 C03C25/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G C09D C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CH 679 310 A (SICPA HOLDING SA) 31 January 1992 (1992-01-31) page 4, line 62 -page 8, line 20 claims 1,4-6,10,13-15,20,21 ---	1-3,5,6, 9,11-13
X	GB 1 493 134 A (UCB SA) 23 November 1977 (1977-11-23) page 1, left-hand column, line 10 -page 3, left-hand column, line 21 example 3 ---	1-3,5,6, 9,11-13
A	US 3 509 234 A (BURLANT WILLIAM J ET AL) 28 April 1970 (1970-04-28) column 1, line 16 -column 4, line 17 example 6 --- -/--	1,2,5,6, 9,11

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone.
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

5 October 1999

Date of mailing of the international search report

15/10/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Neugebauer, U

INTERNATIONAL SEARCH REPORT

International Application No

PCT/NL 99/00423

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 726 162 A (NEW OJI PAPER CO LTD) 14 August 1996 (1996-08-14) page 3, line 34 -page 5, line 36 examples 1,2 -----	1-3,5,6, 11,13

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 99/00423

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
CH 679310	A	31-01-1992	NONE	
GB 1493134	A	23-11-1977	AT 338295 B	10-08-1977
			AT 537375 A	15-12-1976
			AU 8293375 A	13-01-1977
			BE 831185 A	12-01-1976
			BR 7504387 A	06-07-1976
			CH 596285 A	15-03-1978
			DD 120040 A	20-05-1976
			DE 2530896 A	29-01-1976
			FI 751996 A	13-01-1976
			FR 2277863 A	06-02-1976
			IT 1040885 B	20-12-1979
			JP 51125171 A	01-11-1976
			LU 72962 A	31-05-1976
			NL 7508180 A	14-01-1976
			SE 7507866 A	13-01-1976
US 3509234	A	28-04-1970	AU 442845 B	21-11-1973
			AU 1748667 A	15-08-1968
			BE 693267 A	03-07-1967
			DE 1644797 A	24-09-1970
			FR 1513285 A	30-04-1968
			GB 1162722 A	27-08-1969
			GB 1162723 A	27-08-1969
			GB 1162724 A	27-08-1969
			GB 1162721 A	27-08-1969
			NL 6701830 A, B	08-08-1968
EP 0726162	A	14-08-1996	JP 8218295 A	27-08-1996
			DE 69600276 D	18-06-1998
			DE 69600276 T	10-09-1998
			US 5942329 A	24-08-1999

THIS PAGE BLANK (USPTO)